



# AURELIA® DELIGHT CLEAR PD

Powdered Vinyl Examination Gloves

## AURELIA® GLOVES

A SUPERMAX HEALTHCARE BRAND

sales@supermax.co.uk


+441733 615215

Supermax Healthcare Ltd,  
Unit 12-16 Titan Drive  
Fengate, Peterborough  
PE1 5XN

[aureliagloves.co.uk](http://aureliagloves.co.uk)






Regulations	PPE Regulation (EU) 2016/425
Quality Standards	ISO 9001:2015 Quality Management Systems ISO 13485: 2016 Medical Devices Quality Management Systems
Harmonised Standards	EN 420: 2003 + A1: 2009 Protective gloves. General requirements and test methods. BS EN 1186:2002 Materials and articles in contact with foodstuffs.

 10 x 100

**S M L XL**

38826 38827 38828 38829

Sizes & Dimensions	Single wall thickness	Physical Properties												
 <p>S 80+10 mm M 95+10 mm L 110+10 mm XL &gt; 110 mm</p>	 <p>min. 240 mm min. 240 mm min. 240 mm min. 240 mm</p>  <p>① min. 0.05 mm ② min. 0.05 mm ③ min. 0.04 mm</p>	<table border="1"> <thead> <tr> <th></th> <th>Unaged</th> <th>Aged</th> </tr> </thead> <tbody> <tr> <td>Tensile Strength</td> <td>Min. 11.0 MPa</td> <td>Min. 11.0 MPa</td> </tr> <tr> <td>Elongation</td> <td>Min. 350%</td> <td>Min. 350%</td> </tr> <tr> <td>Strength at Break</td> <td>Min. 3.6N</td> <td>Min. 3.6N</td> </tr> </tbody> </table>		Unaged	Aged	Tensile Strength	Min. 11.0 MPa	Min. 11.0 MPa	Elongation	Min. 350%	Min. 350%	Strength at Break	Min. 3.6N	Min. 3.6N
	Unaged	Aged												
Tensile Strength	Min. 11.0 MPa	Min. 11.0 MPa												
Elongation	Min. 350%	Min. 350%												
Strength at Break	Min. 3.6N	Min. 3.6N												



Vinyl



Powdered



3 Years



Smooth



4.5g +/- 0.2g



Clear

